


**MATERIAL DATA SHEET**

Material Reference	AKN66
Description	COMMERCIAL INSERTION RUBBER



Properties	Value
Polymer	NR/SBR
Colour	Black
Quality	Cotton Insertion
Hardness Shore 'A'	65° ± 5° Shore A
Specific Gravity	1.5 ± 0.05 g/cm ³
Tensile Strength (Polymer)	3.5 Mpa
Elongation at Break	200%
Minimum Continuous Working Temperature	-20°C
Maximum Continuous Working Temperature	70°C
Roll/Sheet Width	1400mm

Guidelines for use. (It is the responsibility of the Customer to ensure suitability of use)

AKN66 is reinforced with one or more plies of embedded fabric lattice which helps to prevent tearing. It is suitable for low to medium duty applications involving air, water, diluted mixtures and for economic, general purpose applications. Natural rubber is less resistant to ozone, petroleum oils and fluids than some of the synthetics.

Additional Information

The figures and test data on this datasheet are average values and the result of many years of tests and trials. As the company's products are used for a multiplicity of purposes, and as the company has no control over the method of their application or use, the company excludes all conditions or warranties, expressed or implied by statute or otherwise, as to their products and/or their fitness for any particular purpose. Any technical co-operation between the company and the customer is given for the customer's assistance only and without liability on the part of the company.